

Product Data Sheet White Latex Traffic Marking Paint #11021W

1275 STATE ST, HAMMOND, IN 46320 • (219) 933-0877

PRODUCT DESCRIPTION				PRODUCT CHARACTERISTICS
A 100% acrylic latex regular drying marking paint for concrete, brick, and bituminous surfaces. This product has been designed for painting centerlines, edge lines and auxiliary markings of highways, runways, parking lots, traffic aisles, etc. This product is normally not recommended for restriping.				Vehicle Type: Acrylic Latex Polymer
				Viscosity: 80 to 90 KU
				Weight Solids: 65% minimum
				Volume Solids: 45% minimum
				Density (Weight per Gallon):
Performance Characteristics				13.12 ± 0.20 lbs/gal
Meets Performance Requirements of TT-P-1952B				VOC (minus exempts): 68 g/L
Test Description	Test Method	Requirements	Results	VOC (with exempts): 34 g/L
Color (white)	Fed. Std. 595 #37925	6 CIE Lab	Pass	Dry time: No-Pick-Up: 35 – 45 minutes
Reflectance	ASTM E97	92% minimum	Pass	Dry Through: 75 – 85 minutes
Fineness of Grind	ASTM D1210	3 Hegman min.	Pass	(Note: Applied film thickness, relative humidity and temperature will affect dry time)
Dry Time No-Pick-Up	ASTM D711	75 minutes max.	Pass	Shelf Life: 12 months if unopened and stored in a cool area.
Flexibility	ASTM D522	Pass	Pass	
Freeze-Thaw Resistance	ASTM D2243	5 cycles	Pass	
Accelerated Package Stability	ASTM D1849	<5 Ku change	Pass	THIS PRODUCT DOES NOT CONTAIN MERCURY, LEAD, HEXAVALENT CHROMIUM, TOLUENE, CHLORINATED SOLVENTS, HYDROLYSABLE CHLORINE DERIVATIVES OR CARCINOGENS AS DEFINED IN 29 CFR 1910.1200.
Water Resistance	TT-P-1952B	Pass	Pass	OR CARCINOGENS AS DEFINED IN 29 CFR 1910.1200.
Bleeding Ratio	ASTM D969	0.95 min	Pass	
Scrub Resistance	ASTM D2486	400 cycles	Pass	
Dry Opacity	ASTM D2805	0.95 minimum	Pass	Note: These results represent actual control values when tested under
Abrasion Resistance	ASTM D968	65 liters minimum	Pass	laboratory conditions. To the best of our knowledge, the above technical data is true and accurate at the date of issuance but is subject to change
				without prior notice.

READ AND FOLLOW ALL INSTRUCTIONS AND WARNINGS ON PRODUCT LABELS AND DATA SHEETS.

The following supersedes any provision contained in the forms, letters, and papers of your company. This product is designed and intended for professional application only. All products should be thoroughly tested under application conditions prior to use. The information contained herein is believed to be reliable. HOWEVER, DAVIES IMPERIAL COATINGS MAKES NO WARRANTY CONCERNING THIS PRODUCT, WHETHER EXPRESS OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. UNDER NO CIRCUMSTANCES SHALL DAVIES IMPERIAL COATINGS BE LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL, OR ANY OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH OF WARRANTY, STRICT LIABILITY, OR ANY OTHER LEGAL THEORY, ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT. THE SOLE REMEDY OF THE BUYER AND THE SOLE LIABILITY OF DAVIES IMPERIAL COATINGS FOR ANY CLAIMS SHALL BE LIMITED TO THE BUYER'S PURCHASE PRICE OF THE PRODUCT WHICH IS THE SUBJECT OF THE CLAIM OR THE AMOUNT ACTUALLY PAID FOR SUCH PRODUCT, WHICHEVER IS LESS. TECHNICAL ADVICE FURNISHED BY DAVIES IMPERIAL COATINGS SHALL NOT CONSTITUTE AN EXPRESS WARRANTY, WHICH IS EXPRESSLY DISCLAIMED. ALL TECHNICAL ADVICE GIVEN IS ACCEPTED AT THE RISK OF THE BUYER. CAUTION! VAPOR HARMFUL. HARMFUL OR FATAL IF SWALLOWED. INJURIOUS TO EYES. KEEP OUT OF THE REACH OF CHILDREN! BEFORE using this product, it is essential that the "Safety Data Sheet"



1275 STATE ST, HAMMOND, IN 46320 • (219) 933-0877

Product Data Sheet White Latex Traffic Marking Paint #11021W

WATERBORNE TRAFFIC MARKING F	DAINT ADDITION REQUIREMENTS
SURFACE PREPARATION	Coverage
The surface to be painted must be dry and free of loose paint, grease, oil, and dirt. Striping paints will not adhere to unclean surfaces. New concrete must be allowed to fully cure before painting. Adhesion can be adversely affected by sealers and efflorescence on new concrete. These should be removed by etching, abrasive blasting, or allowing the surface to weather for an extended period of time. New concrete and/or asphalt should be allowed to age for several months before painting. Applying a test stripe to test for adequate cure of new asphalt is recommended.	Coverage is dependent upon user and usage. Normally, approximately 90 square feet per gallon. In terms of striping, approximately 20 gallons will stripe a 4-inch line one mile using a mechanical striper. Using a truck mounted spraying system, approximately 16 gallons will stripe a 4-inch line one mile. Over applying paint may cause "mud cracking" and may affect adhesion and longevity. Under applying paint may cause premature wear off and/or premature fading of color.
THINNING	Spray Equipment
None is normally required, but a small amount of water may be added if needed. DO NOT add gasoline, oil or any other petroleum-based products to waterborne paints. Adding any amount of thinner may adversely affect dry time.	Application equipment must be clean from all previous paint(s). The use of non-stainless steel spray equipment is strongly discouraged as an alkaline paint may "surface shock" when exposed to other mild metals. Only stainless steel or plastic spray equipment should be used.
Application	CLEAN UP
Stir all containers thoroughly before using. Paint only in dry weather. Straining the paint when using spray equipment is recommended. May be applied by a marking machine, roller, or brush. No surface priming is required. Apply to a wet film thickness of 14-16 mils to yield a dry film thickness of 8-10 mils.	Clean all brushes, rollers, tools, and paint lines immediately with warm water and a mild detergent to prevent drying. If drying does occur, a mild caustic solution should remove dried film.
For best results apply at substrate temperatures of 50°F and rising. When using glass beads, 4 - 6 pounds of beads per gallon	Drying Times
is recommended. If spraying, do not mix beads directly into paint. When striping in cold temperatures, the warmer the paint the easier it is to spray. Recommended application conditions: 50°F minimum and 90°F maximum. Apply at least 5	Dry times are dependent upon weather conditions both before and after application. See Product Characteristics for more information.
°F above dew point with a relative humidity below 85%.	HANDLING SAFETY
	Avoid prolonged or repeated contact with skin. Avoid breathing of vapors or spray mist. Do not take internally. Close container after each use. Wear respirator, eye protection and protective clothing when handling. See SDS for further information.

The following supersedes any provision contained in the forms, letters, and papers of your company. This product is designed and intended for professional application only. All products should be thoroughly tested under application conditions prior to use. The information contained herein is believed to be reliable. HOWEVER, DAVIES IMPERIAL COATINGS MAKES NO WARRANTY CONCERNING THIS PRODUCT, WHETHER EXPRESS OR IMPLIED, INCLUDING THE WARRANTES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. UNDER NO CIRCUMSTANCES SHALL DAVIES IMPERIAL COATINGS BE LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL, OR ANY OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH OF WARRANTY, STRICT LIABILITY, OR ANY OTHER LEGAL THEORY, ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT. THE SOLE REMEDY OF THE BUYER AND THE SUBLECLIABILITY OF DAVIES IMPERIAL COATINGS FOR ANY CLAIMS SHALL BE LIMITED TO THE BUYER'S PURCHASE PRICE OF THE PRODUCT WHICH IS THE SUBJECT OF THE CLAIM OR THE AMOUNT ACTUALLY PAID FOR SUCH PRODUCT, WHICHEVER IS LESS. TECHNICAL ADVICE FURNISHED BY DAVIES IMPERIAL COATINGS SHALL NOT CONSTITUTE AN EXPRESSUY DISCLAIMED. ALL TECHNICAL ADVICE GIVEN IS ACCEPTED AT THE RISK OF THE BUYER. CAUTION! VAPOR HARMFUL, HARMFUL OR FATAL IF SWALLOWED, INJURIOUS TO EYES. KEEP OUT OF THE REACH OF CHILDRENI BEFORE using this product, it is essential that the "Safety Data Sheet"

Davies Imperial Coatings, Inc. REVISION DATE: 02/09/2016 DATE PRINTED: 06/22/2021