

PRODUCT DESCRIPTION				PRODUCT CHARACTERISTICS			
A 100% acrylic latex regular drying marking paint for concrete, brick, and bituminous surfaces. This product has been designed for painting centerlines, edge lines and auxiliary markings of highways, runways, parking lots, traffic aisles, etc. This product is normally not recommended for restriping.				Vehicle Type: Acrylic Latex Polymer Viscosity: 80 to 90 KU Weight Solids: 65% minimum Volume Solids: 45% minimum Density (Weight per Gallon): 12.90 ± 0.20 lbs/gal VOC (minus exempts): 67 g/L VOC (with exempts): 34 g/L Dry time: No-Pick-Up: 35 – 45 minutes Dry Through: 75 – 85 minutes <i>(Note: Applied film thickness, relative humidity and temperature will affect dry time)</i> Shelf Life: 12 months if unopened and stored in a cool area.			
PERFORMANCE CHARACTERISTICS				<p align="center">THIS PRODUCT DOES NOT CONTAIN MERCURY, LEAD, HEXAVALENT CHROMIUM, TOLUENE, CHLORINATED SOLVENTS, HYDROLYSABLE CHLORINE DERIVATIVES OR CARCINOGENS AS DEFINED IN 29 CFR 1910.1200.</p> <p>Note: These results represent actual control values when tested under laboratory conditions. To the best of our knowledge, the above technical data is true and accurate at the date of issuance but is subject to change without prior notice.</p>			
Meets Performance requirements of TT-P-1952B							
Test Description	Test Method	Requirements	Results				
Color (yellow)	Fed. Std. 595 #33538	6 CIE Lab	Pass				
Fineness of Grind	ASTM D1210	3 Hegman min.	Pass				
Dry Time No-Pick-Up	ASTM D711	75 minutes max.	Pass				
Flexibility	ASTM D522	Pass	Pass				
Freeze-Thaw Resistance	ASTM D2243	5 cycles	Pass				
Accelerated Package Stability	ASTM D1849	<5 Ku change	Pass				
Water Resistance	TT-P-1952B	Pass	Pass				
Bleeding Ratio	ASTM D969	0.95 min	Pass				
Scrub Resistance	ASTM D2486	400 cycles	Pass				
Dry Opacity	ASTM D2805	0.95 minimum	Pass				
Abrasion Resistance	ASTM D968	65 liters minimum	Pass				

READ AND FOLLOW ALL INSTRUCTIONS AND WARNINGS ON PRODUCT LABELS AND DATA SHEETS.

The following supersedes any provision contained in the forms, letters, and papers of your company. This product is designed and intended for professional application only. All products should be thoroughly tested under application conditions prior to use. The information contained herein is believed to be reliable. **HOWEVER, DAVIES IMPERIAL COATINGS MAKES NO WARRANTY CONCERNING THIS PRODUCT, WHETHER EXPRESS OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** UNDER NO CIRCUMSTANCES SHALL DAVIES IMPERIAL COATINGS BE LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL, OR ANY OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH OF WARRANTY, STRICT LIABILITY, OR ANY OTHER LEGAL THEORY, ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT. THE SOLE REMEDY OF THE BUYER AND THE SOLE LIABILITY OF DAVIES IMPERIAL COATINGS FOR ANY CLAIMS SHALL BE LIMITED TO THE BUYER'S PURCHASE PRICE OF THE PRODUCT WHICH IS THE SUBJECT OF THE CLAIM OR THE AMOUNT ACTUALLY PAID FOR SUCH PRODUCT, WHICHEVER IS LESS. TECHNICAL ADVICE FURNISHED BY DAVIES IMPERIAL COATINGS SHALL NOT CONSTITUTE AN EXPRESS WARRANTY, WHICH IS EXPRESSLY DISCLAIMED. ALL TECHNICAL ADVICE GIVEN IS ACCEPTED AT THE RISK OF THE BUYER. CAUTION! VAPOR HARMFUL. HARMFUL OR FATAL IF SWALLOWED. INJURIOUS TO EYES. KEEP OUT OF THE REACH OF CHILDREN! BEFORE using this product, it is essential that the "Safety Data Sheet" describing the product as well as the "Product Label" be reviewed. If your company does not have such information or has any questions, contact the manufacturer.

WATERBORNE TRAFFIC MARKING PAINT APPLICATION REQUIREMENTS

SURFACE PREPARATION

The surface to be painted must be dry and free of loose paint, grease, oil, and dirt. Striping paints will not adhere to unclean surfaces. New concrete must be allowed to fully cure before painting. Adhesion can be adversely affected by sealers and efflorescence on new concrete. These should be removed by etching, abrasive blasting, or allowing the surface to weather for an extended period of time. New concrete and/or asphalt should be allowed to age for several months before painting. Applying a test stripe to test for adequate cure of new asphalt is recommended.

COVERAGE

Coverage is dependent upon user and usage. Normally, approximately 90 square feet per gallon. In terms of striping, approximately 20 gallons will stripe a 4-inch line one mile using a mechanical striper. Using a truck mounted spraying system, approximately 16 gallons will stripe a 4-inch line one mile. Over applying paint may cause "mud cracking" and may affect adhesion and longevity. Under applying paint may cause premature wear off and/or premature fading of color.

THINNING

None is normally required, but a small amount of water may be added if needed. DO NOT add gasoline, oil or any other petroleum-based products to waterborne paints. Adding any amount of thinner may adversely affect dry time.

SPRAY EQUIPMENT

Application equipment must be clean from all previous paint(s). The use of non-stainless steel spray equipment is strongly discouraged as an alkaline paint may "surface shock" when exposed to other mild metals. Only stainless steel or plastic spray equipment should be used.

APPLICATION

Stir all containers thoroughly before using. Paint only in dry weather. Straining the paint when using spray equipment is recommended. May be applied by a marking machine, roller, or brush. No surface priming is required. Apply to a wet film thickness of 14-16 mils to yield a dry film thickness of 8-10 mils. For best results apply at substrate temperatures of 50°F and rising. When using glass beads, 4 - 6 pounds of beads per gallon is recommended. If spraying, do not mix beads directly into paint. When striping in cold temperatures, the warmer the paint the easier it is to spray. Recommended application conditions: 50°F minimum and 90°F maximum. Apply at least 5 °F above dew point with a relative humidity below 85%.

CLEAN UP

Clean all brushes, rollers, tools, and paint lines immediately with warm water and a mild detergent to prevent drying. If drying does occur, a mild caustic solution should remove dried film.

DRYING TIMES

Dry times are dependent upon weather conditions both before and after application. See Product Characteristics for more information.

HANDLING SAFETY

Avoid prolonged or repeated contact with skin. Avoid breathing of vapors or spray mist. Do not take internally. Close container after each use. Wear respirator, eye protection and protective clothing when handling. See SDS for further information.

The following supersedes any provision contained in the forms, letters, and papers of your company. This product is designed and intended for professional application only. All products should be thoroughly tested under application conditions prior to use. The information contained herein is believed to be reliable. **HOWEVER, DAVIES IMPERIAL COATINGS MAKES NO WARRANTY CONCERNING THIS PRODUCT, WHETHER EXPRESS OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** UNDER NO CIRCUMSTANCES SHALL DAVIES IMPERIAL COATINGS BE LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL, OR ANY OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH OF WARRANTY, STRICT LIABILITY, OR ANY OTHER LEGAL THEORY, ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT. THE SOLE REMEDY OF THE BUYER AND THE SOLE LIABILITY OF DAVIES IMPERIAL COATINGS FOR ANY CLAIMS SHALL BE LIMITED TO THE BUYER'S PURCHASE PRICE OF THE PRODUCT WHICH IS THE SUBJECT OF THE CLAIM OR THE AMOUNT ACTUALLY PAID FOR SUCH PRODUCT, WHICHEVER IS LESS. TECHNICAL ADVICE FURNISHED BY DAVIES IMPERIAL COATINGS SHALL NOT CONSTITUTE AN EXPRESS WARRANTY, WHICH IS EXPRESSLY DISCLAIMED. ALL TECHNICAL ADVICE GIVEN IS ACCEPTED AT THE RISK OF THE BUYER. CAUTION! VAPOR HARMFUL. HARMFUL OR FATAL IF SWALLOWED. INJURIOUS TO EYES. KEEP OUT OF THE REACH OF CHILDREN! BEFORE using this product, it is essential that the "Safety Data Sheet" describing the product as well as the "Product Label" be reviewed. If your company does not have such information or has any questions, contact the manufacturer.