

PRODUCT DESCRIPTION				PRODUCT CHARACTERISTICS			
<p>A moderately fast drying chlorinated marking paint for concrete, brick, and bituminous surfaces. This product has been designed for painting centerlines, edge lines and auxiliary markings of highways, runways, crosswalks, stop zones, parking lots, storage zones, traffic aisles, etc.</p>				<p>Vehicle Type: Chlorinated Rubber Alkyd Blend</p> <p>Viscosity: 78 to 82 KU</p> <p>Weight Solids: 70% minimum</p> <p>Volume Solids: 49% minimum</p> <p>Density (Weight per Gallon): 11.92 ± 0.20 lbs/gal</p> <p>VOC (minus exempts): 142 g/L</p> <p>VOC (with exempts): 86 g/L</p> <p>Dry time: No-Pick-Up: <10 minutes Dry Through: <25 minutes <i>(Note: Applied film thickness, relative humidity, and temperature will affect dry time)</i></p> <p>Shelf Life: 12 months if unopened and stored in a cool area.</p>			
PERFORMANCE CHARACTERISTICS				<p>THIS PRODUCT DOES NOT CONTAIN MERCURY, LEAD, HEXAVALENT CHROMIUM, HALOGENATED SOLVENTS, NOR ANY CARCINOGEN, AS DEFINED IN 20 CFR 1910.1200.</p> <p>Note: These results represent actual control values when tested under laboratory conditions. To the best of our knowledge, the above technical data is true and accurate at the date of issuance but is subject to change without prior notice.</p>			
Test Description	Test Method	Requirements	Results				
Fineness of Grind	ASTM D1210	3 Hegman min.	Pass				
Dry Time No-Pick-Up	ASTM D711	10 minutes max.	Pass				
Flexibility	ASTM D522	Pass	Pass				
Consistency	ASTM D562	70 - 85 Ku	Pass				
Accelerated Package Stability	ASTM D1849	<5 Ku change	Pass				
Water Resistance	ASTM D1306	Pass	Pass				
Bleeding Ratio	ASTM D969	0.90 min	Pass				
Dry Opacity	Fed-Std-141	0.92 min	Pass				
Accelerated Weathering	ASTM G53	Pass	Pass				

READ AND FOLLOW ALL INSTRUCTIONS AND WARNINGS ON PRODUCT LABELS AND DATA SHEETS.

The following supersedes any provision contained in the forms, letters, and papers of your company. This product is designed and intended for professional application only. All products should be thoroughly tested under application conditions prior to use. The information contained herein is believed to be reliable. **HOWEVER, DAVIES IMPERIAL COATINGS MAKES NO WARRANTY CONCERNING THIS PRODUCT, WHETHER EXPRESS OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** UNDER NO CIRCUMSTANCES SHALL DAVIES IMPERIAL COATINGS BE LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL, OR ANY OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH OF WARRANTY, STRICT LIABILITY, OR ANY OTHER LEGAL THEORY, ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT. THE SOLE REMEDY OF THE BUYER AND THE SOLE LIABILITY OF DAVIES IMPERIAL COATINGS FOR ANY CLAIMS SHALL BE LIMITED TO THE BUYER'S PURCHASE PRICE OF THE PRODUCT WHICH IS THE SUBJECT OF THE CLAIM OR THE AMOUNT ACTUALLY PAID FOR SUCH PRODUCT, WHICHEVER IS LESS. TECHNICAL ADVICE FURNISHED BY DAVIES IMPERIAL COATINGS SHALL NOT CONSTITUTE AN EXPRESS WARRANTY, WHICH IS EXPRESSLY DISCLAIMED. ALL TECHNICAL ADVICE GIVEN IS ACCEPTED AT THE RISK OF THE BUYER. **CAUTION: DANGER! FLAMMABLE! VAPORS MAY CAUSE FLASH FIRE. VAPOR HARMFUL. HARMFUL OR FATAL IF SWALLOWED. INJURIOUS TO EYES. KEEP OUT OF THE REACH OF CHILDREN!** BEFORE using this product, it is essential that the "Safety Data Sheet" describing the product as well as the "Product Label" be reviewed. If your company does not have such information or has any questions, contact the manufacturer.

SOLVENTBORNE TRAFFIC MARKING PAINT APPLICATION REQUIREMENTS

SURFACE PREPARATION

The surface to be painted must be dry, free of grease and oil and brushed free of loose dirt. Striping paints will not adhere to unclean surfaces or to loose or peeling paint. Over freshly applied/cured surfaces, a test stripe is recommended to determine if the substrate has aged sufficiently prior to application. If the asphalt is insufficiently cured, applying a thin coat (approximately ½ the recommended thickness) generally reduces the extent of lifting and cracking. Concrete curing compounds could affect performance. A test stripe is recommended to determine if the substrate has aged sufficiently prior to application.

APPLICATION PROCEDURES

Application equipment must be clean from all previous paint(s). Stir all containers thoroughly before using. May be applied by spray equipment, brush, or roller. Straining the paint when using spray equipment is recommended. Paint only in dry weather. Higher humidity levels and lower temperatures (air, surface, and material) will increase dry time. Weather conditions after the application could also have an adverse effect on performance. Recommended application conditions: 40° F minimum and 90° F maximum, at least 5° F above dew point and a maximum of 85% RH. Apply to a wet film thickness of 12 - 15 mils. Using proper equipment will maximize proper film build, coverage, and performance. Protect painted surfaces from traffic until thoroughly dry. Painted surfaces may become slippery when wet. Dry times are dependent upon weather and surface conditions as well as film thickness and product type.

COVERAGE

Coverage is dependent upon user and usage. Normally, approximately 90 square feet per gallon. In terms of striping, approximately 20 gallons will stripe a 4-inch line one mile using spray equipment. Over applying paint may cause “mud cracking” and may affect adhesion and longevity. Under applying paint may cause premature wear off and/or premature fading of color.

HANDLING SAFETY

DO NOT SMOKE WHILE USING THESE PRODUCTS. These products contain extremely flammable solvents. Keep away from open flame. Close and seal container after each use. Empty containers may still contain flammable vapors and should be treated the same as full containers. Avoid prolonged or repeated contact with skin. Avoid breathing of vapors or spray mist. Do not take internally. Wear respirator, eye protection and protective clothing when handling. Store in a cool dry place, do not store outdoors or in direct sunlight. See SDS for further information.

THINNING

Coating is to be applied without thinning. **DO NOT ADD GASOLINE** or any other petroleum-based products. No thinning is recommended, as it can adversely affect film build, appearance, and adhesion.

CLEAN UP

Clean all brushes, rollers, tools, and spray equipment immediately with toluene or equivalent to prevent drying. Comply with all Federal, State and Local requirements for disposal of paints and related materials.

The following supersedes any provision contained in the forms, letters, and papers of your company. This product is designed and intended for professional application only. All products should be thoroughly tested under application conditions prior to use. The information contained herein is believed to be reliable. **HOWEVER, DAVIES IMPERIAL COATINGS MAKES NO WARRANTY CONCERNING THIS PRODUCT, WHETHER EXPRESS OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** UNDER NO CIRCUMSTANCES SHALL DAVIES IMPERIAL COATINGS BE LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL, OR ANY OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH OF WARRANTY, STRICT LIABILITY, OR ANY OTHER LEGAL THEORY, ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT. THE SOLE REMEDY OF THE BUYER AND THE SOLE LIABILITY OF DAVIES IMPERIAL COATINGS FOR ANY CLAIMS SHALL BE LIMITED TO THE BUYER'S PURCHASE PRICE OF THE PRODUCT WHICH IS THE SUBJECT OF THE CLAIM OR THE AMOUNT ACTUALLY PAID FOR SUCH PRODUCT, WHICHEVER IS LESS. TECHNICAL ADVICE FURNISHED BY DAVIES IMPERIAL COATINGS SHALL NOT CONSTITUTE AN EXPRESS WARRANTY, WHICH IS EXPRESSLY DISCLAIMED. ALL TECHNICAL ADVICE GIVEN IS ACCEPTED AT THE RISK OF THE BUYER. **CAUTION: DANGER! FLAMMABLE! VAPORS MAY CAUSE FLASH FIRE. VAPOR HARMFUL. HARMFUL OR FATAL IF SWALLOWED. INJURIOUS TO EYES. KEEP OUT OF THE REACH OF CHILDREN!** BEFORE using this product, it is essential that the "Safety Data Sheet" describing the product as well as the "Product Label" be reviewed. If your company does not have such information or has any questions, contact the manufacturer.