



## DIRECT FIRE PARKING LOT SEALANT

No. JTS-006

Revision: 001

### DESCRIPTION

Direct Fire Parking Lot Sealant is formulated with selected asphaltic resins, synthetic polymeric rubber, plasticizers, stabilizers, and a blend of organic reinforcing fillers.

This construction grade material is a hot applied, one part sealer that provides excellent results under extremely varying conditions. Direct Fire Parking Lot Sealant is perfect for use in applications that are susceptible to tracking and picking up, such as pedestrian foot traffic and vehicle power steering.

- *Good bonding characteristics*
- *Weather resistant*
- *Passes multiple freeze and thaw cycles*

### SPECIFICATIONS

- Local Municipal Codes

### TYPICAL PROPERTIES

Recommended Pour Temperature	400 °F
Maximum Heating Temperature	450 °F
Recommended Extended Heating	6 Hours
Penetration (150gr/5 sec.)	45
Flow, 140 °F	3 mm max.
Resilience	40 %
Asphalt Compatibility	Compatible

### USE AND APPLICATIONS

Direct Fire Parking Lot Sealant is recommended for sealing of joints and cracks in concrete and asphaltic pavements and parking lots. It is designed for use in sealing expansion and contraction joints as well as random cracks.

- Parking Lots • Plaza Decks • Driveways

### FEATURES AND BENEFITS

- Construction grade joint and crack sealing compound for concrete and asphaltic pavements.
- Economical and effective preventative maintenance treatment.
- Actually prolongs the pavement service life.
- Seals cracks and joints from water penetration.

### EQUIPMENT

Use an agitated oil-jacketed or direct fired unit that has separate temperature gauges for both the sealant and the heat transfer fluid. Take the 30 lb. plastic bag of sealant and load into the kettle one at a time. Melt only enough material for the day's activities. Once melted, additional material can be added as needed. Material can be safely reheated within the sealants service life.

**NOTE: Prolonged heating of the sealant above the maximum safe heating temperature may cause it to gel in the kettle.**

### JOINT PREPARATIONS

To facilitate proper adhesion, the joint or crack should be dry and clear of any dirt, dust or other contaminants. Substrate and ambient temperatures must be 40°F or above. Proper sizing of the joint will cause the maximum extension/compression to not exceed 50% of the width. Joints or random cracks of ¼" or less are difficult to properly clean prior to applying the sealant.

### SERVICE LIFE

The service life ("pot-life") at application temperatures is approximately 12 hours. Adding fresh material to the melter as sealant is being used will extend the service life. Material that has been overheated can thicken and gel in the melter. Any material that has exceeded the service life should be removed from the melter and discarded.

### COVERAGE

Width	Depth	Pounds/100 lineal feet
3/8"	3/8"	6.9
3/8"	1/2"	9.3
1/2"	1/2"	12.3
1/2"	1"	24.7
3/4"	1/2"	18.6
3/4"	3/4"	27.8

### PACKAGING

60# CARTON (2 SPLIT 30# CUBES)  
36 CARTONS PER PALLET